



# HP Xtreme

Film	T	VLT	VLR	SET	SER	SEA	UVT	GR	SC	E	UF	TSER
HPX 5	1.5mil	5%	5%	20%	12%	68%	<1%	94%	0.46	0.73	1.06	61%
HPX 20	1.5mil	20%	6%	32%	9%	59%	<1%	78%	0.56	0.79	1.09	51%
HPX 40	1.5mil	39%	8%	48%	7%	48%	<1%	57%	0.68	0.85	1.12	42%

T : Thickness VLT : Visible Light Transmittance VLR : Visible Light Reflectance SET : Solar Energy Transmittance SER : Solar Energy Reflectance SEA : Solar Energy Absorbance UVT : Ultra Violet Transmittance GR : Glare Reduction SC : Shading Coefficient E : Emissivity UF : U Factor (BTU /HR./SQ.FT.) TSER : Total Solar Energy Rejection