



# CS Xtreme

Film	T	VLT	VLR	SET	SER	SEA	UVT	GR	SC	E	UF	TSER
<b>CSX5</b>	1.5mil	6%	6%	44%	7%	49%	<1%	93%	0.66	0.89	1.12	42%
<b>CSX 20</b>	1.5mil	19%	6%	47%	6%	47%	<1%	79%	0.69	0.89	1.12	40%
<b>CSX 30</b>	1.5mil	30%	6%	53%	6%	41%	<1%	67%	0.74	0.89	1.12	36%
<b>CSX 40</b>	1.5mil	39%	6%	56%	6%	38%	<1%	57%	0.77	0.89	1.12	33%

T : Thickness VLT : Visible Light Transmittance VLR : Visible Light Reflectance SET : Solar Energy Transmittance SER : Solar Energy Reflectance SEA : Solar Energy Absorbance UVT : Ultra Violet Transmittance GR : Glare Reduction SC : Shading Coefficient E : Emissivity UF : U Factor (BTU /HR./SQ.FT.) TSER : Total Solar Energy Rejection