



# CC Xtreme

Film	T	VLT	VLR	SET	SER	SEA	UVT	GR	SC	TSER	IR Rejections
<b>CCX 5</b>	2mil	4%	6%	11%	6%	83%	<1%	96%	.39	66%	76%
<b>CCX 18</b>	2mil	18%	6%	16%	6%	78%	<1%	82%	.40	62%	76%
<b>CCX 33</b>	2mil	32%	7%	23%	6%	71%	<1%	65%	.49	58%	76%
<b>CCX 42</b>	2mil	42%	7%	28%	6%	66%	<1%	54%	.54	53%	78%
<b>CCX 70</b>	2mil	69%	8%	37%	7%	56%	<1%	24%	.61	47%	85%
<b>CCX 86</b>	1.5mil	86%	9%	65%	8%	27%	<1%	6%	.83	27%	35%

**T:** Thickness    **VLT:** Visible Light Transmittance    **VLR:** Visible Light Reflectance    **SET:** Solar Energy Transmittance  
**SER:** Solar Energy Reflectance    **SEA:** Solar Energy Absorbance    **UVT:** Ultra Violet Transmittance  
**GR:** Glare Reduction    **SC:** Shading Coefficient    **TSER:** Total Solar Energy Rejection