



IR Xtreme

Film	T	VLT	VLR	SET	SER	SEA	UVT	GR	SC	TSER	IR Rejection
IRX 70	2.0 Mil	70%	7%	0.35	7%	58%	<1%	24%	0.59	49%	88%
IRX 40	1.5 Mil	41%	9%	0.21	8%	71%	<1%	55%	0.47	59%	92%
IRX 28	1.5 Mil	29%	8%	0.17	8%	75%	<1%	68%	0.44	62%	92%
IRX 19	2.0 Mil	19%	8%	0.11	10%	82%	<1%	78%	0.38	67%	92%

T : Thickness VLT : Visible Light Transmittance VLR : Visible Light Reflectance SET : Solar Energy Transmittance SER : Solar Energy Reflectance SEA : Solar Energy Absorbance UVT : Ultra Violet Transmittance GR : Glare Reduction SC : Shading Coefficient
 TSER: Total Solar Energy Rejection